

PAT-NO: JP406200101A

DOCUMENT-IDENTIFIER: JP 06200101 A

TITLE: CHLOROSULFONATED POLYOLEFINIC RESIN
COMPOSITION

PUBN-DATE: July 19, 1994

INVENTOR-INFORMATION:

NAME

KIRA, SATOSHI

TANAKA, TETSUTADA

ASSIGNEE-INFORMATION:

NAME

SHOWA DENKO KK

COUNTRY

N/A

APPL-NO: JP04348484

APPL-DATE: December 28, 1992

INT-CL (IPC): C08L023/28, C08K003/34 , C08K005/14 ,
C08K009/04 , C08L023/34

ABSTRACT:

PURPOSE: To obtain a chlorosulfonated polyolefinic resin composition, excellent in moldability and good in appearance of moldings.

CONSTITUTION: This chlorosulfonated polyolefinic resin composition is obtained by blending 100 pts.wt. resin composition composed of (A) 50-90 pts.wt. chlorosulfonated polyolefin and (B) 50-10 pts.wt. chlorinated polyethylene with (C) 20-150 pts.wt. clay, having 0.1-1.0 μ m average particle diameter and treated with a mercapto-based silane coupling

agent, (D) 0.5-20
pts. wt. organic peroxide and (E) 0.1-10 pts.wt.
polyfunctional compound.

COPYRIGHT: (C)1994, JPO&Japio